



PRIME COAT 4200 CHEMKOTE

DESCRIPTION:

PRIME COAT 4200 is a two component, 100% solids, high chemical resistant epoxy coating.

APPLICATIONS:

Coating concrete, steel, or wood where high chemical resistance is needed.
Primary or Secondary containment.

ADVANTAGES:

Highly Chemical Resistant
Moisture Insensitive
Won't Blush
High Gloss
USDA Approved

PACKAGING:

1-1/2 Gallon Units
3 Gallon Units
15 Gallon Units

PHYSICAL PROPERTIES AT 77° F (25° C)

MIX RATIO A:B	2:1 By Volume
---------------	---------------

VISCOSITY	10,000 c.p.s.
-----------	---------------

COLOR	Gray or Red
-------	-------------

POT LIFE	100 gram mass	1 gallon mass	Tack Free (20 mils)
----------	---------------	---------------	---------------------

90° F (32° C)	3 hrs	1 hr, 15 min	10 hrs
---------------	-------	--------------	--------

73° F (23° C)	47 min	40 min	4 hrs, 45 min
---------------	--------	--------	---------------

50° F (10° C)	25 min	21 min	1 hr, 30 min
---------------	--------	--------	--------------

COVERAGE	(10 mils)	160 square feet per gallon
	(20 mils)	80 square feet per gallon

TEST DATA (STRENGTHS REPORTED IN P.S.I.)

COMPRESSIVE STRENGTH	ASTM D-695	7,700
COMPRESSIVE MOE	ASTM D-695	2.74×10^5

TENSILE STRENGTH	ASTM D-638	2,900
TENSILE MOE	ASTM D-638	3.08×10^5

ELONGATION	ASTM D-638	1.4%
------------	------------	------

SHORE HARDNESS	D SCALE	80
----------------	---------	----

WATER ABSORPTION	ASTM D-570	1%
------------------	------------	----

APPLICATION TECHNIQUES:

MATERIAL CONDITIONING: Pre condition materials 65° - 85° F (19° - 30° C) before using.

SURFACE PREPARATION: Surface must be clean and free of any dust, oil, grease, laitance, curing compounds, or any other contaminants. This should be achieved by shotblasting, sandblasting, or some other mechanical means.

MIXING CONSIDERATIONS: Pre mix each component. Measure exactly 2 parts "A" to 1 part "B" by volume into a clean pail. Only mix the amount of material that can be used within the pot life. Mix epoxy for three minutes using a low speed drill with a mixing paddle (never mix by hand). Scrape the sides and bottom of the pail while mixing. Transfer material to a clean pail halfway through the mixing process.

NOTE: Large batches of epoxy will set up much faster than small batches.

INSTALLING MATERIAL:

Primer: Prime Resins' Water Based Epoxy Primer is recommended. Apply at a rate of 200 square feet per gallon to increase bonding and help eliminate off gassing of Prime Coat 4200.

Coating: Material may be applied by brush or roller. Prime Coat 4200 should be applied at a rate of 160 square feet per gallon. Two coats minimum are required. The second coat may be applied at a rate of 80 square feet per gallon for extra protection. Prime Coat 4200 may be thinned using Xylene at a maximum rate of one pint per gallon of mixed epoxy.

Flooring: Pour mixed material onto concrete and pull out to desired millage using a notched squeegee and backroll.

Use a steel spiked roller to remove any entrapped air from the coating. Wear shoes with spikes to avoid slipping or damaging the system.

Apply the second coat after first coat is tack free but within 36 hours. If first coat cures longer than 36 hours, the surface must be roughed up by light brush blasting or sand paper.

A "maintenance system" may be installed by using Prime Coat 4200 "Red" for the first coat and "Gray" for the second coat. When the red begins to show through, it is time to re-coat with the gray material.

USE ONLY HIGH QUALITY ROLLER COVERS. USE 3/8" MOHAIR NAP (CANDY STRIPE) WITH PHENOLIC CORE.

- LIMITATIONS:** Minimum application temperature is 40° F (5° C) and rising.
Minimum age of concrete must be 28 days.
Coating will chalk and yellow under direct exposure to sunlight.
- STORAGE:** Store in a dry environment at a temperature between 40° to 90° F (4° to 32° C).
Ideal temperature range is 65° to 75° F (18° to 24° C). Temperatures below 60° F (16° C) will cause epoxy to thicken making it difficult to properly blend the components. Under proper conditions, the shelf life is twelve (12) months in unopened, damage-free containers. **PROTECT FROM MOISTURE. DO NOT ALLOW PRODUCT TO FREEZE.**
- WARNINGS:** "A" material may cause skin irritation. Contains epoxy resins.
"B" material may cause severe burns on skin. Contains amines.
- FIRST AID:** **Skin Contact** - Wipe off contaminated area and wash with soap and water.
Eye Contact - Immediately flush eyes with large amounts of water for 10 minutes. Get medical attention.
Inhalation - Move to fresh air if symptoms occur. If breathing is difficult, get medical attention.
Ingestion - If conscious give two glasses of milk or water. Get medical attention.
See MSDS for more information.
- CLEAN UP:** Clean equipment with MEK or Xylene immediately after use. Clean skin with soap and water. Wash contaminated clothing before re-use.
- WARRANTY:** Prime Resins warrants its products to be free from manufacturing defect and that products meet the published characteristics when tested in accordance with ASTM and Prime Resins standards. No other warranties by Prime Resins are expressed or implied, including no warranty of merchantability or fitness for a particular purpose. Prime Resins will not be liable for damages of any sort resulting from any claimed breach of warranty. Prime Resins' liability under this warranty is limited to replacement of material or refund of the sales price of the material. There are no warranties on any product that has exceeded the "shelf life" or "expiration date" printed on the package label.

If you have any questions or comments about any of Prime Resins products or application techniques you may contact us directly at 800-321-7212, Monday through Friday 8:00 AM to 5:00 PM Eastern Standard Time.

TDS-4200-08/05



"Innovations in Infrastructure Repair Technology"

2291 Plunkett Road • Conyers, Georgia 30012

770-388-0626 / 800-321-7212 • Fax: 770-388-0936 • www.primeresins.com • email: sales@primeresins.com