

Prime Bond 3000 High Mod

High-strength multi-purpose epoxy binding adhesive

Description

Medium-viscosity, high-strength epoxy bonding agent for bonding new concrete to old or mixing with dry sand to make a repair mortar. USDA approved. This is a two-component, 100% solids, amine-cured epoxy resin adhesive that conforms to ASTM C-881 type II.

Primary Applications

- Bonding new “plastic” concrete to existing concrete or steel
- Binder for epoxy repair mortar to patch, overlay horizontal surfaces
- Gravity feed cracks in horizontal concrete and wood
- Bonding materials such: concrete, masonry, stone, wood, metal, etc.
- Anchoring dowel bars, bolts, pins, etc. in horizontal surfaces
- Machinery base plate grout

Advantages

- High compressive, bond, tensile and flexural strengths
- Moisture insensitive
- Good chemical resistance
- USDA approved

Packaging

- 2 gallon unit

Technical information: Physical properties at 73°F (23°C) - Liquid

Properties will vary depending upon site conditions, application method, mixing method and equipment, material temperature, and curing conditions.

Viscosity: 8,000 cps

Color: concrete gray

| Pot Life | 100 grams | 1 gallon | Tack free—20 mils |
|-------------|--------------|-------------|-------------------|
| 90°F (32°C) | 32 min | 22 min | 4 hrs 30 min |
| 73°F (23°C) | 42 min | 36 min | 5 hrs 20 min |
| 50°F (10°C) | 2 hrs 30 min | 1 hr 30 min | 7 hrs 20 min |

| Test results | | |
|-----------------------------------|--------------|------------|
| Compressive strength | 11,070 | ASTM D-695 |
| Compressive modulus of elasticity | 370,000 | ASTM D-695 |
| Tensile strength | 3,480 | ASTM D-638 |
| Tensile modulus of elasticity | 429,000 | ASTM D-638 |
| Tensile elongation | 1.2% | ASTM D-638 |
| Bond strength (dry cure) - 2 day | 3,390 | ASTM C-882 |
| Bond strength (dry cure) - 14 day | 3,600 | ASTM C-882 |
| Shore hardness | 86 D | D scale |
| Heat deflection | 120°F (49°C) | ASTM D-648 |
| Water absorption | < 1% | ASTM D-570 |

Technical Datasheet



| Test results (cont.) | |
|----------------------|---|
| Coverage | 80 square feet per gallon at 20 mils |
| Coverage | .370 cubic feet per gallon when mixed with 3 parts by volume Prime Blend sand |

Accessory Products

Prime Blend sand

Directions For Use

Mixing Ratio: A:B 1:1 by volume

Manual Mixing: Only mix the amount of material that can be used within the pot life. To prevent bubble formation, avoid introduction of air into mixed material by controlling drill speed and mixing method. Thoroughly mix materials using a low speed drill with a mixing paddle. Scrape the sides and bottom of the pail while mixing. Note: Larger batches exotherm and set up faster than small batches

Pump Application: This product is ideally suited for use the Quick Mix cartridge system. 10 gallon units are packaged for use with extruder pump equipment.

Material Preparation: Store material overnight to precondition to 70-80° F (21-27°C) prior to use. Pre-mix each component prior to combining. "B" component contains pigments, fillers, and other chemicals the settle over time. Failure to properly pre-mix will result in uncured or improperly cured material.

Bonding Requirements: Apply neat mixed material to surface by brush, roller or spray. Pour new concrete while material is still tacky. If it loses tackiness or cures for more than 24 hours before new concrete is poured, roughen surface by light brush or sanding followed by a solvent wipe before recoating with fresh material.

Limitations: Cold temperatures will slow down reaction time and increase viscosity. Do not use below 40°F (4°C). Material that is off ratio or not mixed thoroughly will not cure to full strength and may remain tacky indefinitely.

Storage & Clean Up

Storage: Store in dry environment between 40 and 80°F (4 and 27°C). Do not allow to freeze. Shelf Life: 1 year from date of manufacture in unopened containers properly stored. Protect from moisture.

Clean Up: Clean off skin with soap and water immediately. Clean uncured material from tools with Prime Flex Eco Flush.

Environmental Protection

Cured material is environmentally safe. Dispose of in according to appropriate regulations. Clean up any spilled catalyzed liquid material and dispose of according to local, state and federal regulations.

Shipping

Shipping Class: Motor Freight Class 60

Hazard Classification: ORM-D

Health & Safety

Safety: "B" component contains amines and may cause severe burns upon skin contact for any length of time. Use OSHA-approved personal protective equipment (PPE), including safety glasses, gloves and confined space equipment/procedures if applicable. Avoid skin contact; do not ingest. See SDS for complete safety precautions. For professional use only .

First Aid

Eye Contact: Immediately flush with large amounts of water.

Seek medical attention. **Inhalation:** Move to fresh air if symptoms occur. If breathing is difficult, seek medical attention. **Ingestion:** Seek medical attention immediately.

Skin Contact: Wipe off contaminated area and wash with soap and water immediately.

Manufacturing

Products manufactured by Prime Resins, Inc. in U.S.A. under strict quality assurance practices at our Conyers, GA plant.

Warranty & Disclaimer

Prime Resins, Inc. warrants its products to be free from manufacturing defects and that products meet the published characteristics when tested in accordance with ASTM and Prime Resins standards. No other warranties by Prime Resins, Inc. are expressed or implied, including no warranty of merchantability or fitness for a particular purpose. Prime Resins, Inc. will not be liable for damages of any sort resulting from any claimed breach of warranty. Prime Resins' liability under this warranty is limited to replacement of material or refund of sales price of the material. There are no warranties on any product that has exceeded the "shelf life" or "expiration date" printed on the package label.

Rev. 11/4/2021